

**NEW CLAIMS 9-16**

---

9. The colloid silica slurry wherein hydrogen peroxide from 5 to 100 ppm is added and pH is from 6.0 to 8.0.

10. The colloidal silica slurry as claimed in claim 9, wherein said colloidal silica is the lowered metal colloidal silica produced from silicate ester.

11. The colloidal silica slurry as claimed in claim 9, wherein metal content of said colloidal silica is 1 ppm or less.

12. The colloidal silica slurry as claimed in claim 10, wherein metal content of said colloidal silica is 1 ppm or less.

a' 13. The colloidal silica slurry as claimed in claim 9, wherein pH is from 6.5 to 7.5.

14. The colloidal silica slurry as claimed in claim 9, wherein additional quantity of hydrogen peroxide is from 10 to 50 ppm.

15. The colloidal silica slurry as claimed in claim 9, wherein an average particle diameter of said colloidal silica is from 5 to 300 nm.

16. The colloidal silica slurry as claimed in claim 9, wherein an average particle diameter of said colloidal silica is from 10 to 250 nm.

---